















## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	100% Splitface
	<b>PATTERN</b>	Natural Course Heights   2:1 Random Ashlar
	<b>HEIGHTS</b>	Varies from 2" - 9" (Full Bed); 2"-9" (Thin Veneer)
	<b>LENGTHS</b>	Random, 8"-36" (Full Bed); 8"-24" (Thin Veneer; crated/palletized material can exceed 20")
	<b>DEPTHS</b>	3/4" to 1-1/4" (Thin Veneer); 3"-5" (Full Veneer)
	<b>COLORS</b>	Buff , Cream , Gray - Grey , Tan
	<b>COVERAGE</b>	Full Bed Depth Veneer: 35-40 Square Feet Per Ton Also Available in Thin Veneer
	<b>WEIGHT</b>	14 pounds per square foot (Thin Veneer)
	<b>FLATS</b>	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	<b>CORNERS</b>	10 l/f Box; 100 l/f Crate; 100 l/f Pallet
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	1.60 psi
Bulk Specific Gravity	2.54 psi

### ASTM C-170

Parallel to Rift, Dry	15100 psi
Parallel to Rift, Wet	13200 psi
Perpendicular to Rift, Dry	15100 psi
Perpendicular to Rift, Wet	14400 psi

### ASTM C-99

Parallel to Rift, Dry	1110 psi
Parallel to Rift, Wet	1110 psi

### ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	2060 psi



**GOLD QUARRY**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101